

DIAMOND LAPPING COMPOUNDS




Diamond Lapping Compounds

Our diamond lapping compounds are manufactured under the strictest controls, assuring you consistent quality results, each and every time.

Fast stock removal and super fine finishes are achieved in less time, for all of your hand or machine lapping of tool steels, carbide and ceramic applications.

Order Number	Concentration	Size	Colour	U.S.B.S Number	Mesh Size	Use	Micro Finish
17068	Standard						10 to 6
17069	Medium	170/200	Orange			Best for	R.M.S.
17070	Heavy					Heavy	
17071	Standard					Stock	8 to 5
17072	Medium	230/325	Red			Removal	R.M.S.
17073	Heavy						
17074	Standard	36 to					7 to 4
17075	Medium	54	Brown	45	325	Most	R.M.S.
17076	Heavy	Micron				Common	
17077	Standard	22 to				Grades	5 to 3
17078	Medium	36	Yellow	30	600	For	R.M.S.
17079	Heavy	Micron				First	
17080	Standard	12 to				Step	4 to 2
17081	Medium	22	Green	15	1,200	Finishing	R.M.S.
17082	Heavy	Micron					
17083	Standard	8 to					3 to
17084	Medium	12	Blue	9	1,800	Final	2 R.M.S.
17085	Heavy	Micron				Finishing	
17086	Standard	4 to	Light			Grades	2 1/2 to
17087	Medium	8	Green	6	3,000	For	3 R.M.S.
17088	Heavy	Micron				Most	
17089	Standard	2 to				Molds And	2 to 1 1/2
17090	Medium	4	Lavender	3	4,000	Dies	R.M.S
17091	Heavy	Micron					
17092	Standard	1 to					1 1/2 to
17093	Medium	3	Pink	2	7,000	Used For	2 R.M.S
17094	Heavy	Micron				Precise	
17095		0 to 2	Blue/			Finishes	
		Micron	Green	1	14,000	And	1
17096		0 to 1	Grey	1/2	50,000	High	or
		Micron				Polishing	Less
17097		0 to 1/2	Tan	1/4	Finer than 50,000		R.M.S.



Graff

Email: info@graffdiamond.com

DIAMOND LAPPING COMPOUNDS